

Vilamul Copolymer Emulsions & Acrylic Polymers

Vinyl Acetate Copolymer Emulsions

VILAMUL REF. NO.	POLYMER TYPE	STABILISED	SOLIDS	VISCOSITY 10RPM (mPas, Brookfield RV#3)	VISCOSITY 50RPM (mPas, Brookfield RV#3)	pH	S.G.	MFFT °C	T.G. °C
099	VA / Acrylate	Colloid / Surfactant	51.5 - 53.5	250 - 1000	100 - 750	4.2 - 5.2	1.06	8 - 10	14.5
101	VA / Acrylate	Colloid / Surfactant	54 - 56	1000 - 3000	400 - 1300	4.0 - 6.0	1.07	10 - 11	19.5
124	VA / Acrylate	Colloid / Surfactant	55.5 - 57.5	2000 - 5000	700 - 1600	4.2 - 5.2	1.07	0	5.5
395	VA / Acrylate	Colloid / Surfactant	54 - 56	2000 - 5000	700 - 1600	4.2 - 5.2	1.07	11 - 12	21.5
605	VA / Veova / Acrylate	Colloid / Surfactant	51.5 - 53.5	1500 - 3000	500 - 1500	4.2 - 5.2	1.06	9 - 11	14.8

Acrylic Polymers

VILACRYL REF. NO.	POLYMER TYPE	STABILISED	SOLIDS	VISCOSITY 10RPM (mPas, Brookfield RV#3)	VISCOSITY 50RPM (mPas, Brookfield RV#3)	pH	S.G.	MFFT °C	T.G. °C
800	Acrylic	Colloid / Surfactant	47 - 49	50 - 1000	50 - 500	7.0 - 9.0	1.04	0 - 5	-3.5
1000	Acrylic	Colloid / Surfactant	47 - 49	50 - 1000	50 - 500	7.0 - 9.0	1.04	29	36



VIL
RESINS

EST. 1938

For more information:
+44(0)1204 388800
enquiries@vilresins.co.uk
vilresins.co.uk