

# Vilkyd Wood Coating Resins

## Wood Coating Resins

VILKYD REF. NO.	% NON- VOLATILE CONTENT	SOLVENT	VISCOSITY @ 25°C (POISE)	% NON- VOLATILE @ 2 POISE	% FATTY ACID	FATTY ACID / OIL TYPE	ESTERIFYING AGENT	PRINCIPAL USES
205X60	60	Xylene	90-110	44	34	Linoleic Rich	Mixed	Versatile resin for A/C lacquers, stoving or air dry finishes.
209FH85	85	IMS / BA	40-50	70	50	Linoleic Rich	Pentaerythritol	Fast curing wood finishes with excellent stability.
714IP70	70	Isopropanol	20-40	58	40	Linoleic Rich	Mixed	Fast curing wood finishes with outstanding durability

We summarise our most popular solvent based resins. All grades can be offered in alternative solvents or at different solids contents.

For further information please contact a member of our technical or sales staff.